



TECHNICAL DATA SHEET

AG-1007 Fine Line Silver Conductive Ink

DESCRIPTION

- Screen printable ink for fine line traces
- Can be printed on ITO for touchscreen or EL applications
- Can be thinned with solvent for spraying or dipping for EMI/RFI shielding applications
- Extremely tough, scuff resistant, crease resistant and has excellent adhesion to polyester, polyimide and most other substrates.
- Designed to give a good balance between long open time on screens and short drying time in subsequent drying processes.
- Compatible with our UV curable dielectrics, all of our conductive epoxy adhesives and our UV curable component encapsulants and conformal coatings.
- AG-1007 can be blended with C-100 carbon resistive ink to give intermediate resistivity ranges.

Applied Ink Solutions can adjust the rheology of AG-1007 to allow for more open time or quicker drying to accommodate different screening and drying operations.

AG-1007 is designed for screen printing in:

- flex circuit
- membrane switch
- touch screens
- other printed electronic applications

Where fine line/pitch printing is required.

TYPICAL PROPERTIES

Appearance	Thixotropic silver colored paste
Viscosity SC4-14 spindle @ shear 10, 25° C	7,250- 8,950 cps
Drying Time	90 seconds to 4 minutes at 130°C (depending upon air flow and oven heat profile)
Total % NV Solids	70.3% +/- 1%
Hegman Gauge	<10.0 μ
Surface Resistivity	< .1Ω/square /mil when fully dried
Shelf Life	6 months in unopened container

AG-1007 Fine Line Silver Conductive Ink

Application Guidelines

AG-1007 will thicken when it is stored in sealed containers over a period of time. It is essential to mix the material thoroughly before use to redisperse any settled silver particles and to return the ink to a more desirable viscosity.

Screening

A stainless steel (190 to 400mesh) screen is recommended, with emulsion thickness between .001" and .004". A polyurethane squeegee with a Shore 'A' durometer between 60 and 70 is recommended.

Thinning & Cleanup

Use Solvent 20 or Solvent 30 for thinning. For cleanup, use Solvent 10 or suitable screen cleaner. If faster drying time is required, contact Applied Ink Solutions for solvent recommendations. If solvent based inks are left on screens for any length of time, the ink will gradually thicken as solvent evaporates. If ink is to be left on an inactive press for any length of time, solvent evaporation can be minimized by pooling the ink into a small area instead of leaving it spread out over a large area. Pooling the ink reduces the surface area, thus slowing the drying process. Always check the viscosity of ink that has been recovered from a screen and add small amounts of solvent while mixing thoroughly to restore viscosity. Solvent can be added to reclaim thickened ink as long as the ink has not dried and hardened completely.

Drying

It is essential that all residual solvent be removed from this ink once it is applied. Incomplete drying will cause the ink to appear dry on the surface while trapping solvent underneath the surface. Over time, this trapped solvent will migrate out of the ink, and can cause adhesion problems with any material, such as dielectrics, applied over the ink.

Completeness of Drying

Evaluate the point-to-point resistance along one of the screened conductive paths after one pass through the drying oven or one cycle in a batch-drying oven. Run the substrate through another drying cycle. Measure the point-to-point resistance again along the same path and compare it to the original reading. If the resistance decreases by less than 10%, then the ink is essentially dry after the first drying cycle or pass through the oven. If the resistance decreases by more than 10%, then more drying time is required to completely remove the solvent.

Health & Safety

Products manufactured by Applied Ink Solutions are intended for use in an industrial environment by trained personnel. Please follow proper health/safety processes regarding storage, handling and processing of the products.

Guidelines are intended to provide a starting point for evaluation. Applied Ink Solutions recognizes that each customer's manufacturing process is unique, and we are available to provide technical assistance to resolve your processing issues. Call us to discuss your application in more detail.

The properties are accurate to the best of our knowledge and Applied Ink Solutions makes no guarantees for customer specifications established in applications where this product is used. Customer assumes responsibility for determining fitness of use in their particular application.